

Digital Visual Standard 外观检查标准




75474

Digital Visual Standard

外观检查标准

<u>REV</u> 版本	<u>DATE</u> 日期	<u>DESCRIPTION OF CHANGES</u> 变更描述	<u>REVISED BY</u> 修订者	<u>REVIEWED /</u> <u>APPROVED BY</u> 确认者
A	01/16/2014	DVS Created	E. Jaramillo	E. Jaramillo
B	3/25/2014	Revise DVS for clarification and consistency with similar part 75924	C. Robuck	C. Robuck
C	12/10/2015	Add rubber crack defect inspection	Tony .Yang	Mike.Lu
D	8/21/2022	Update	Weiting Liu	P. Pan

DVS 75474-外观检查标准



**BLISTER
ACCEPTABLE**

箭头所指的这种气疤
是可以接受的

**CHECK DATE STAMP
PLUG - MUST BE SET
FOR CURRENT
MONTH & YEAR** 确认
生产日期是否在当月



DVS 75474-外观检查标准




**BLISTER/AIR TRAP ON
END OF SNOOT
ACCEPTABLE**

箭头所指的圆圈末尾处的气泡和
空气造成的小缺口OK

**ONE BLISTER IN
THIS AREA
ACCEPTABLE**

箭头所指的区域有两个(小
于或等于于两个)气疤OK



DVS 75474-外观检查标准



**DISTORTION
REJECT**

变形, 不良

PLEX CODE: DISTORTION-变形

**FLASH
REMOVE**

箭头所指的飞边要拿掉

PLEX CODE: EXCESS FLASH-多余飞边



DVS 75474-外观检查标准



**FLASH IN WIRE TIE HOLE -
FLASH MUST BE BROKEN**


箭头所指的这个孔一定要弄破

PLEX CODE: EXCESS FLASH-多余飞边

**FLASH IN WIRE TIE HOLE -
FLASH MUST BE BROKEN**

箭头所指的这个孔一定要弄破

PLEX CODE: EXCESS FLASH-多余飞边



DVS 75474-外观检查标准



TEAR

REJECT

撕裂, 不良


PLEX CODE: TORN/TEARS-撕裂

OPEN BLISTER/KNIT LINE

REJECT

硫痕/炸开的气疤, 不良

PLEX CODE: LITE, NON-FILL-融合线,
缺料



DVS 75474-外观检查标准



SMALL DEFORMATION/NON-FILL ON
1ST OR 2ND SEAL RIB ACCEPTABLE,
BUT ONE RIB HAS TO BE DEFECT
FREE

第一道或第二道密封圈变
形、缺胶，OK。必须保证
有一道密封圈是没有缺陷
的

DVS 75474-外观检查标准



**LUBE APPLIED
CORRECTLY
ACCEPTABLE
必须涂上润滑剂**

**NO LUBE
APPLICATION
REJECT不涂润滑
剂的视为不良**

PLEX CODE: Missed Lube-漏涂油



DVS 75474-外观检查标准




SMALL TORN/ NON-FILL
IN GROMMET
APPLICATION
ACCEPTABLE

小的开裂、缺胶，可以
接受（参考极限样件）



DVS 75474-外观检查标准



如图位置（碗口内边缘及内边缘下部）：

- 气疤数量为2
- 气疤不张口，
- 不在密封部位，是可放行产品

如图位置（碗口内边缘及内边缘下部）：

- 气疤数量大于2
- 气疤开口
- 气疤处于密封部位是报废产品。



DVS 75474-外观检查标准



SMALL
DISTORTION
ACCEPTABLE

小的变形，可以接受

如图位置（碗口内边缘及内边缘下部）：

- 气疤数量为2
- 气疤不张口，
- 不在密封部位，是可放行产品

