PRODUCTION PART APPROVAL PROCESS
Performance test results

Supplier **CEMET YAPIŞKAN BANTLAR SAN VE TİC A.Ş.**	Part number **1810A (19 mm x 30 m Black)**
Control Definition	Part Name **BEZ BANT**

Ref. No		SPEC	Test Results			Average	OK	NOK
5.1	Tensile Strength (N/cm)	≥ 55 N/cm	76	78	77	77	√	
5.2	Elongation At Break(%)	≥ 8 %	40	43	43	42	√	
5.3	Adhesion To Steel (N/cm)	≥ 3.0 N/cm	3,28	3,3	3,25	3,27	√	

Print Name	Signature	Title	Date
M.Ömer KARAKURT		Quality Supervisor	29.04.2025